



ARIHANT CHEMICAL CORPORATION & J.J ENTERPRISE

For paints / inks / plastic / Rubber industries Raw material available with us under self import / Manufacturing / Trading.

Specifiction :- EVATANE[®] 42-60

Ethylene – Vinyl Acetate (VA) copolymer with high VA content

DESCRIPTION

EVATANE[®] 42-60 is a random copolymer of Ethylene and Vinyl Acetate made by high-pressure radical polymerization process.

TYPICAL PROPERTIES

Characteristics	Value	Unit	Test Method
Vinyl Acetate content	>41	% Wt	FTIR (Internal Method)
Melt Index (190°C / 2.16 kg)	65-85	g/10min	ISO 1133 / ASTM D1238
Density (23°C)	0.96	g/cm ³	ISO 1183
Melting point	48	°C	ISO 11357-3
Vicat softening point (10N)	<40	°C	ISO 306 / ASTM D1525
Ring & Ball temperature	95	°C	ASTM E28 / NF EN 1238
Elongation at break	900-1100	%	ISO 527 / ASTM D638
Tensile strength at break	5	MPa	ISO 527 / ASTM D638
Hardness Shore A	42	-	ISO 868 / ASTM D2240

APPLICATIONS

The high Vinyl Acetate content of **EVATANE[®] 42-60** brings softness, flexibility, polarity and high solubility. **EVATANE[®] 42-60** can be readily dissolved into various solvents and be used in inks or solvent-base adhesives formulations.

For more detailed information and recommendations regarding your specific application, please contact your local ARKEMA technical representative.

Regd Off: - Plot no 24 Block no .5, 1st floor, Behind Aurora cinema , opp Sahakari bhandar, Matunga (C.R) Mumbai – 400019

Administration /correspondence Office :- Plot No. 319,Room No.3, Ranchoddas Terrace building ,sir Bhalchandra Road, opp Hira House, Near Chhatre Maternity Hospital, Matunga (C.R) Mumbai – 400019

Tel :- +91 22 24148378 / 24146390

Mob :- MR NILESH MEHTA +91 9820142066 / +91 8850378208/+91 9029042066

Email Id :- info@arihantchemcorp.com, or nilesh@arihantchemcorp.com



ARIHANT CHEMICAL CORPORATION & J.J ENTERPRISE

For paints / inks / plastic / Rubber industries Raw material available with us under self import /
Manufacturing / Trading.

Specifiction :- EVATANE[®] 42-60

PROCESSING

EVATANE[®] 42-60 can be processed on most conventional equipments used for thermoplastics. It is recommended to avoid melt temperatures above 230°C and to purge the equipment after a run is completed. **EVATANE[®] 42-60** is soluble in aromatic solvents as toluene up to 35%, benzene up to 25% at room temperature. It is partially soluble up to 15% in MEK, MIBK and DIBK, and insoluble in alcohols.

STORAGE, HANDLING AND SAFETY

EVATANE[®] 42-60 should be stored in standard conditions and protected from UV-light. Improper storage conditions may cause degradation and could have consequences on physical properties of the product. Due to its physical properties (Vicat temperature <40°C), it may be possible that the product shows some caking. This is particularly true during summer time.

Safety data sheet as well as information on handling and storage of the **EVATANE[®] 42-60** is available upon request to your ARKEMA representative or on the web site evatane.com.

SHELF LIFE

Two years from the date of delivery, in unopened packaging. For any use above this limit, please refer to our technical services.

The products described in the brochure are not Medical grades designated for Medical Device applications. Arkema has implemented an internal Medical Policy regarding the use of Arkema products in Medical Devices applications that are in contact with the body or circulating bodily fluids. Arkema has designated Medical grades to be used for such Medical Device applications. Products that have not been designated as Medical grades are not authorized by Arkema for use in Medical Device applications that are in contact with the body or circulating bodily fluids. In addition, except for limited cases as determined by the Medical Device Policy, Arkema strictly prohibits the use of any Arkema products in Medical Device applications that are implanted in the body or in contact with bodily fluids or tissues for greater than 30 days.

For any use of Arkema's product in Medical Device applications, please contact Arkema's sales network.

The statements, technical information and recommendations contained herein are believed to be accurate as of the date hereof. Since the conditions and methods of use of the product and of the information referred to herein are beyond our control, ARKEMA expressly disclaims any and all liability as to any results obtained or arising from any use of the product or reliance on such information; NO WARRANTY OF FITNESS FOR ANY PARTICULAR PURPOSE, WARRANTY OF MERCHANTABILITY OR ANY OTHER WARRANTY, EXPRESS OR IMPLIED, IS MADE CONCERNING THE GOODS DESCRIBED OR THE INFORMATION PROVIDED HEREIN. The information provided herein relates only to the specific product designated and may not be applicable when such product is used in combination with other materials or in any process. The user should thoroughly test any application before commercialization. Nothing contained herein constitutes a license to practice under any patent and it should not be construed as an inducement to infringe any patent and the user is advised to take appropriate steps to be sure that any proposed use of the product will not result in patent infringement.

Regd Off: - Plot no 24 Block no .5, 1st floor, Behind Aurora cinema , opp Sahakari bhandar, Matunga (C.R)
Mumbai – 400019

Administraction /correspondence Office :- Plot No. 319,Room No.3, Ranchoddas Terrace building ,sir
Bhalchandra Road, opp Hira House, Near Chhatre Maternity Hospital, Matunga (C.R) Mumbai – 400019

Tel :- +91 22 24148378 / 24146390

Mob :- MR NILESH MEHTA +91 9820142066 / +91 8850378208/+91 9029042066

Email id :- info@arihantchemcorp.com, or nilesh@arihantchemcorp.com