

# DOW-MITSUI POLYCHEMICALS CO., LTD.

Shiodome City Center  
5-2. Higashi Shim bashi 1-chome  
Minalo ku. Tnkyo 1US 7 22, Japan

TEL: 81-3-6253-4006

FAX: 81-3-6253-4262

## *EVAFLEX EV 40W*

Property	Test Method	Units	EV40LW
VA Content	JIS K7192	wt%	41
MFR	JIS K7210	g/10min	65
Density	JIS K7112	Kg/m <sup>3</sup>	970
Tensile Strength	JIS K7161	MPa	3
Elongation	JIS K7161	%	< 1000
Stiffness	JIS K7106	MPa	1
Hardness(Shore A)	JIS K7215	Degree	49
Vicat Softening Point	JIS K7206	°C	> 30
Melting Point	JIS K7121	°C	40-45

The data shown are typical values and should not be used for specifications.



Dow-Mitsui Polychemicals